

# RUST-AID #163011

## Aerosol Rust Converter & Primer



### Features:

- Any iron or steel surface restored to a "like new" appearance
- For car, trucks, trailers, railings, furniture and tools
- Prevents rust from reappearing
- Resists moisture

### Description:

RUST-AID can be applied to any iron or steel surface to penetrate rust and turn it into a protective black coating. This protective coating will be resistant to moisture and prevents future rust growth. Just remove any loose rust, then apply it like a primer to rusted surfaces. Greatly reduces time spent wire brushing and sanding. A topcoat is required for maximum rust protection.



### Applications:

- Vehicles
- Trailers
- Fences
- Railings
- Sheet Metal
- Storage Tanks

### Product Characteristics:

Appearance:	Aerosol
Odor:	Aromatic
Boiling Point:	-44°C (-47.2°F)
Auto Igniting:	Product is not self-igniting
Lower Explosion Limit:	1.7 Vol %
Upper Explosion Limit:	10.9 Vol %
Relative Density:	Between 0.77 & 0.85 (Water equals 1.00)
Flash Point:	-19°C (-2.2°F)
Evaporation Rate:	Not applicable
pH:	Not determined
Storage Temperature:	40-100°F
Application Temperature:	50-90°F
Water:	0.0%
Resin System:	Chain Stopped Alkyd
Coverage:	Up to 12 square feet
Cleanup:	Paint or lacquer thinner
Shelf life:	Guaranteed for 2 years
Storage:	Store in a well-ventilated place. Store locked up. Protect from sunlight. Do not expose to temperatures exceeding 50°C/122°F.
<b>Transport Information:</b>	
UN Number:	UN1950
Proper Shipping Name:	Aerosols, flammable
Class:	2.1
Packing Group:	--

### Directions:

1. For best results, use when can is between 50°F and 90°F (10°C and 32°C).
2. Shake can at least one minute after rattle is heard and occasionally during use.
3. Use a wire brush or sandpaper to remove as much loose and flaky rust as possible.
4. Spray surface with steady even strokes at a distance of 8 to 12 inches. A chemical reaction will cause the rust to turn black. Allow 24 hours before applying a second coat or when topcoating with a different coating.
5. If clogging develops, turn sprayhead ¼ turn or remove and clean sprayhead slot. DO NOT stick pin or other objects into can opening. With can and sprayhead pointed away from you, reinsert sprayhead with a gentle twisting motion.
6. To clear sprayhead for future use, turn can upside down and spray for 3 seconds. Completely empty cans may be recycled or disposed of with regular trash. Dispose partially empty cans responsibly. DO NOT incinerate or compact.

### Dry Time\*:

To touch - 10 minutes  
To recoat/topcoat - 24 hours

\*At 72°F, 50% humidity,  
1.5 mil thickness

\*\*Curing/Recoat time is extended with multiple coats and excessively thick coats\*\*

**Gloss\*:** Flat, <15

\*as measured on a 60 degree gloss meter

### Pictograms:



### Signal Word:

DANGER

### Personal Protective Equipment Required:



### VOC Compliant:

Not available.

### DOT Placard:

