

# LITHO-LUBE II 65T #2723

## Lithium Complex Multi-Purpose Grease



### Features:

- Dropping point 500°F (260°C) (ASTM D566)
- Meets (ASTM D4950)
- Excellent pressure resistance
- Excellent shearability, shelf life, water resistance & anti-corrosion properties
- Timken OK Load of 65 LBS
- Temperature Range: 0°F to 300°F (-18°C to 150°C)
- NLGI 2
- Lithium complex thickener
- Contains Moly Pro EP additive for extreme pressure and anti-wear advantages, without leaving the dirty residue
- Base Oil: Mineral Oil
- Available in tubes (272301) & 35lb pails (272335)



### Description:

LITHO-LUBE II 65T is a **Lithium Complex EP** formulated as a wide-ranging multi-purpose grease with excellent extreme pressure resistance, shearability, shelf life, water resistance, and anti-corrosion properties, offering the additional protection to meet today's high-performance requirements.

### Applications:

- Mining Equipment
- Golf Courses
- Industrial Plants
- Wheel Bearings
- Steering Linkages
- Roller Bearings
- Presses
- Pivot Points
- Steering Knuckles
- Oilfield
- Semi-Truck
- Quarry
- Axle Assemblies
- Spring Pins
- Plain Bearing
- Winches
- Bushings
- Snow Blowers
- Off-Road Construction
- Automotive
- Ball Roller
- Universal Joints
- King Pins
- Thrust Bearings
- Electric Motors
- Bus & County Barns
- Chassis Lubrication
- Marine
- Refinery
- Pumps
- Pivot Pins
- Ball Joints
- Gears
- Latches
- Hinges
- Slides
- Agriculture
- Bus, Train, Railroad, Subway
- Sleeve Bearings
- Fifth-Wheel Hitch Plate
- Water Pump Bearings
- Mowers, Tractors
- Couplings
- Farm Equipment
- Tie-Rod Ends

### Product Characteristics:

Appearance:	Amber semi-solid, mild odor
Color:	Amber
Odor:	Mild Odor
Solubility (water):	Insoluble in water, soluble in alcohols and petroleum distillates
Relative Density:	0.9
Flash Point:	235°C (455°F) (Cleveland open cup)
Viscosity:	Cone penetration (ASTM D217) 265-295
NLGI	2
Penetration (ASTM D217):	265-295
Base Oil:	Mineral
Base Oil Viscosity:	451 cSt at 40°C
Base Oil Viscosity:	28 cSt at 100°C
Thickener:	Lithium complex
4-Ball EP weld point, kg:	500
4-Ball wear scar, mm:	0.5
Timken OK Load:	65
Specific Gravity:	0.9
Density (lb/gal):	7.5
Dropping Point (ASTM D566):	>500°F (260°C)
Storage:	Store in cool dry area in original or equivalent container in accordance with all regulations. Do not expose to extreme heat or flame. Store below 65°C (150°F), away from strong oxidizers and acids.
<b>Transport Information:</b>	
UN Number:	Not regulated
Proper Shipping Name:	Not regulated
Class:	Not regulated
Packing Group:	Not regulated

### Directions:

Pump in grease until all old grease comes out. For best results, it is advisable that old grease be removed prior to application.

**DO NOT USE ON OXYGEN SERVICE.**

**Signal Word:** None.

### Pictograms:



### Personal Protective Equipment Required:



### DOT Placard:

Not regulated as dangerous goods or hazardous material.